



Sivic® Z760

Product Specification
 Date Issued: 01/10/05
 Supercedes: 12/04/03

Description: Sivic Z760 is a fully fluxed polyblend of 45% ACN NBR/PVC (70/30). It is produced via a mechanical technology, which provides a lump-free homogenous polymer.

<i>Packaging:</i> Sivic Z760 shall be supplied in the form of amber colored slabs free from foreign material considered objectionable for normal applications. Net weight per unit: 2204 lbs (1 MT).			
Specification	Min.	Max.	Test Procedure No. ⁽¹⁾
<i>Polymer Properties</i>			
Mooney Viscosity, MS (1+4) @100°C ⁽³⁾	49	61	ISO 289
Specific Gravity	1.075	1.095	ISO 2781
<i>Special Notes:</i> Refer to the appropriate MSDS for proper safety, handling and storage instructions. (1) Test Procedures are available upon request. (2) Shelf Life – Retest critical parameters 2 years after date of manufacture. (3) Tentative specification			
<i>Reason for Issue:</i> 1) Specific Gravity range changed from (1.05-1.09) to (1.075 to 1.095)			



Zeon Chemicals L.P., 4111 Bells Lane, Louisville, KY 40211 Phone: 877-ASK ZEON, Fax: 502-775-2055

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Zeon Chemicals L.P. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond the direct control of Zeon Chemicals L.P. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.